

Having thus described the invention, what is claimed as new and secured by Letters Patent is:

Claims

**BEST AVAILABLE COPY**

1. A method of increasing the carbonation capacity of an alkaline earth metal sorbent for reaction with carbon dioxide wherein alkaline earth metal oxide is produced during the calcination of an alkaline earth metal carbonate in the fluidized bed oxidation of combustion fuels, comprising hydrating particles of alkaline earth metal oxide to form particles of alkaline earth metal hydroxide at a suitable temperature and pressure; and carbonating the particles of alkaline earth metal hydroxide to form particles of alkaline earth metal carbonate.
2. The method as defined in claim 1 wherein hydration of the alkaline earth metal oxide particles is performed using liquid water or steam at a temperature greater than 50°C.
3. The method as defined in claim 1 wherein calcination of the alkaline earth metal carbonate is performed at a temperature in the range of 700°C to 1200°C.
4. The method as defined in claim 2 wherein hydration of the alkaline earth metal oxide particles is performed at atmospheric pressure.
5. The method as defined in claim 2 wherein hydration of the alkaline earth metal oxide particles is performed at a pressure greater than atmospheric pressure.
6. The method as defined in claim 1 wherein the alkaline earth metal carbonate is limestone.
7. The method as defined in claim 1 wherein the alkaline earth metal oxide is lime.

## BEST AVAILABLE COPY

8. The method as defined in claim 1 wherein the fluidized bed for combustion comprises a pressurized fluidized bed combustor (PFBC/C).
9. The method as defined in claim 1 wherein the fluidized bed for combustion comprises a circulating fluidized bed combustor (CFBC/C).
10. A method of increasing the carbonation capacity of an alkaline earth metal sorbent for reaction with carbon dioxide wherein alkaline earth metal oxide is produced during the calcination of alkaline earth carbonate in the fluidized bed oxidation of combustion fuels, for reaction with carbon dioxide comprising:
  - (a) introducing a suitable calcinable material into a fluidized bed;
  - (b) calcining the calcinable material to form an alkaline earth metal oxide and carbon dioxide;
  - (c) pretreating particles of the alkaline earth metal oxide in a hydration reactor at a suitable temperature and pressure to form particles of alkaline earth metal hydroxide;
  - (d) carbonating the alkaline earth metal hydroxide to produce alkaline earth metal carbonate and water;
  - (e) calcining the alkaline earth metal carbonate to regenerate the alkaline earth metal oxide and produce carbon dioxide;
  - (f) carbonating the alkaline earth metal oxide in a carbonator at elevated temperature such that the alkaline earth metal oxide captures the carbon dioxide to produce an alkaline earth metal carbonate;
  - (g) re-introducing the carbonated alkaline earth metal carbonate into the fluidized bed; and
  - (h) calcining the carbonated alkaline earth metal carbonate to regenerate the alkaline earth metal oxide;
  - (i) and repeating steps (c) to (g) utilizing the product of step (h).
11. The method as defined in claim 10 wherein the carbon dioxide produced in steps (b) and (e) is pure carbon dioxide.

## BEST AVAILABLE COPY

12. The method as defined in claim 10 wherein spent sorbent and uncaptured carbon dioxide is recovered in step (f).
13. The method as defined in claims 10 wherein hydration of the alkaline earth oxide particles is performed using liquid water or steam at a temperature greater than 50°C.
14. The method as defined in claim 10 wherein calcination of the alkaline earth metal carbonate is performed at a temperature in the range of 700°C to 1200°C.
15. The method as defined in claim 13 wherein hydration of the alkaline earth metal oxide particles is performed at atmospheric pressure.
16. The method as defined in claim 13 wherein hydration of the alkaline earth metal oxide particles is performed at a pressure greater than atmospheric pressure.
17. The method as defined in claim 10 wherein the alkaline earth metal carbonate is limestone.
18. The method as defined in claim 10 wherein the alkaline earth metal oxide is lime.
19. The method as defined in claim 10 wherein the fluidized bed for combustion comprises a pressurized fluidized bed combustor (PFBC/C).
20. The method as defined in claim 10 wherein the fluidized bed for combustion comprises a circulating fluidized bed combustor (CFBC/C).